

TEST REPORT

Report No.: LCS190618129AR

Date:2019.08.08

Page 1 of 15

Applicant : JCC Lighting Products Limited
Address : Innovation Centre, Beeding Close, Southern Cross Trading Estate, Bognor Regis, West Sussex PO22 9TS

Report on the submitted samples said to be:

Sample Name : FG2 Fixed/Tilt IP20 Downlight

Trade Mark : JCC, ACEL, Avenue

Client's information : N/A

Style No. : JC94113BN, JC94113CH, JC94113WH, AC43840, AC43860, AC43870, AVGU13UFR CH, AVGU13UFR SC, JC94114BN, JC94114CH, JC94114WH, AC44404, AC44406, AC44407, AVGU14UFR WH, AVGU13UFR WH, AVGU14UFR SC, AVGU14UFR CH

Testing Period : June 25, 2019 ~ August 08, 2019

Results : Please refer to next page(s).

TEST REQUEST	CONCLUSION
<p>According to the customer's request, based on the performed tests on submitted sample, the result of Lead, Cadmium, Mercury, Hexavalent Chromium, PBBs, PBDEs, Dibutyl Phthalate(DBP), Benzylbutyl Phthalate(BBP), Bis(2-ethylhexyl) Phthalate(DEHP), Diisobutyl phthalate(DIBP) content comply with the limit as set of RoHS Directive (EU) 2015/863 amending Annex II to Directive 2011/65/EU.</p>	<p style="text-align: center; color: blue;">Pass</p>

Signed for and on behalf of LCS



TEST REPORT

Report No.: LCS190618129AR

Date:2019.08.08

Page 2 of 15

Results:
A.EU RoHS Directive 2011/65/EU and its amendment directives on XRF
Test method: With reference to IEC 62321-3-1:2013, Screening by X-ray Fluorescence Spectroscopy (XRF)

Seq. No.	Tested Part(s)	Results						Date of sample submission/resubmission
		Cd	Pb	Hg	Cr [▼]	Br [▼]		
						PBBs	PBDEs	
1	Green metal sheet	X	BL	BL	X	/	/	2019-06-25
2	Green plastic sheet	BL	BL	BL	BL	BL	BL	2019-06-25 2019-07-23
3	Black plastic sheet	BL	BL	BL	BL	BL	BL	2019-06-25 2019-07-23
4	White plastic sheet	BL	BL	BL	BL	BL	BL	2019-06-25 2019-07-23
5	Silver metal sheet	BL	BL	BL	BL	/	/	2019-06-25
6	White plastic sheet	BL	BL	BL	BL	BL	BL	2019-06-25 2019-07-23
7	Red plastic sheet	BL	BL	BL	BL	BL	BL	2019-06-25 2019-07-23 2019-08-05
8	Ferrous metal sheet	BL	BL	BL	BL	/	/	2019-06-25
9	Silver metal sheet	BL	BL	BL	BL	/	/	2019-06-25
10	White metal sheet	BL	BL	BL	X	/	/	2019-06-25
11	Silver metal sheet	BL	BL	BL	X	/	/	2019-06-25
12	White ceramics	BL	BL	BL	BL	BL	BL	2019-06-25
13	Silver plastic sheet	BL	BL	BL	BL	BL	BL	2019-06-25
14	Silver metal spring	BL	BL	BL	X	/	/	2019-06-25
15	Golden metal sheet	BL	BL	BL	BL	/	/	2019-06-25
16	Silver metal sheet	BL	BL	BL	BL	/	/	2019-06-25
17	Golden metal needle	BL	BL	BL	BL	/	/	2019-06-25
18	White plastic sleeve	BL	BL	BL	BL	BL	BL	2019-06-25
19	Brown plastic line	BL	BL	BL	BL	BL	BL	2019-06-25
20	Blue plastic line	BL	BL	BL	BL	BL	BL	2019-06-25
21	Silver wire	BL	BL	BL	BL	/	/	2019-06-25
22	Silver metal screw	BL	BL	BL	BL	/	/	2019-06-25

TEST REPORT

Report No.: LCS190618129AR

Date:2019.08.08

Page 3 of 15

Seq. No.	Tested Part(s)	Results						Date of sample submission/resubmission
		Cd	Pb	Hg	Cr ^v	Br ^v		
						PBBs	PBDEs	
23	Silver metal screw	BL	BL	BL	BL	/	/	2019-06-25
24	Silver metal screw	BL	BL	BL	BL	/	/	2019-06-25
25	Silver metal spring	BL	BL	BL	X	/	/	2019-06-25
26	Silver metal sheet	BL	BL	BL	X	/	/	2019-06-25
27	White plastic sheet	BL	BL	BL	BL	X	X	2019-06-25
28	White plastic sheet	BL	BL	BL	BL	BL	BL	2019-06-25
29	Silver metal sheet	BL	BL	BL	BL	/	/	2019-06-25
30	Beige ceramics	BL	BL	BL	BL	BL	BL	2019-06-25
31	Silver plastic sheet	BL	BL	BL	BL	BL	BL	2019-06-25
32	Grey Metal Spring	BL	BL	BL	BL	/	/	2019-06-25
33	Silver metal sheet	BL	BL	BL	BL	/	/	2019-06-25
34	White plastic sleeve	BL	BL	BL	BL	BL	BL	2019-06-25
35	Silver metal sheet	BL	BL	BL	X	/	/	2019-06-25
36	Golden metal needle	BL	BL	BL	BL	/	/	2019-06-25
37	Brown plastic line	BL	BL	BL	BL	BL	BL	2019-06-25
38	Blue plastic line	BL	BL	BL	BL	BL	BL	2019-06-25
39	Silver wire	BL	BL	BL	BL	/	/	2019-06-25

TEST REPORT

Report No.: LCS190618129AR

Date:2019.08.08

Page 4 of 15

Note:

- (1) Results were obtained by XRF for primary screening, and further chemical testing by ICP (for Cd, Pb, Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs) are recommended to be performed, if the concentration exceeds the below warning value according to IEC 62321-3-1:2013.

Element	Unit	Non-metal	Metal	Composite Material
Cd	mg/kg	BL≤70-3σ<X <130+3σ≤OL	BL≤70-3σ<X <130+3σ≤OL	BL≤50-3σ<X <150+3σ≤OL
Pb	mg/kg	BL≤700-3σ<X <1300+3σ≤OL	BL≤700-3σ<X <1300+3σ≤OL	BL≤500-3σ<X <1500+3σ≤OL
Hg	mg/kg	BL≤700-3σ<X <1300+3σ≤OL	BL≤700-3σ<X <1300+3σ≤OL	BL≤500-3σ<X <1500+3σ≤OL
Cr	mg/kg	BL≤700-3σ<X	BL≤700-3σ<X	BL≤500-3σ<X
Br	mg/kg	BL≤300-3σ<X	--	BL≤250-3σ<X

Note:

- BL = Below Limit
OL = Over Limit
X = Inconclusive

- (2) The XRF screening test for RoHS elements – The reading may be different to the actual content in the sample be of non-uniformity composition.
- (3) The maximum permissible limit is quoted from the document 2015/863/EC amending RoHS directive 2011/65/EU:
- (4) ▼=For restricted substances PBBs and PBDEs, the results show the total Br content; The restricted substance was Cr(VI), and the results showed the total Cr content

TEST REPORT

Report No.: LCS190618129AR

Date:2019.08.08

Page 5 of 15

RoHS Restricted Substances	Maximum Concentration Value (mg/kg) (by weight in homogenous materials)
Cadmium (Cd)	100
Lead (Pb)	1000
Mercury (Hg)	1000
Hexavalent Chromium (Cr(VI))	1000
Polybrominated biphenyls (PBBs)	1000
Polybrominated diphenylethers (PBDEs)	1000
Dibutyl Phthalate(DBP)	1000
Benzylbutyl Phthalate(BBP)	1000
Bis(2-ethylhexyl) Phthalate(DEHP)	1000
Diisobutyl phthalate(DIBP)	1000

Disclaimers:

This XRF Screening report is for reference purposes only. The applicant shall make its/his/her own judgment as to whether the information provided in this XRF screening report is sufficient for its/his/her purposes.

The result shown in this XRF screening report will differ based on various factors, including but not limited to, the sample size, thickness, area, surface flatness, equipment parameters and matrix effect (e.g. plastic, rubber, metal, glass, ceramic etc.). Further wet chemical pre-treatment with relevant chemical equipment analysis are required to obtain quantitative data.

TEST REPORT

Report No.: LCS190618129AR

Date:2019.08.08

Page 6 of 15

B. EU RoHS Directive 2011/65/EU and its amendment Directives 2015/863/EU on Lead, Cadmium, Mercury, Hexavalent Chromium, PBBs, PBDEs, DBP, BBP, DEHP, DIBP content.

Test method:

Lead(Pb) & Cadmium(Cd) Content:

With reference to IEC 62321-5:2013, by acid digestion and analysis was performed by inductively coupled plasma atomic emission spectrometer (ICP-OES)

Mercury(Hg) Content:

With reference to IEC 62321-4:2013+AMD1:2017 CSV, by acid digestion and analysis was performed by inductively coupled plasma atomic emission spectrometer (ICP-OES)

Hexavalent Chromium(Cr⁶⁺) Content:

With reference to IEC 62321-7-1:2015 or IEC 62321-7-2:2017, by alkaline digestion and analysis was performed by UV-visible spectrophotometer (UV-Vis)

PBBs & PBDEs Content:

With reference to IEC 62321-6:2015, by solvent extraction and analysis was performed by gas chromatographic-mass spectrometer (GC-MS)

BBP DBP DEHP & DIBP Content:

With reference to IEC 62321-8:2017, by solvent extraction and analysis was performed by gas chromatographic-mass spectrometer (GC-MS)

1) The test results of Lead Cadmium (Cd)

Item	Unit	MDL	Results			Limit
			(1)	(10)	(11)	
Cadmium Content (Cd)	mg/kg	2	N.D.			1000

2) The test results of Hexavalent Chromium (Cr⁶⁺)(metal)

Item	Unit	MDL	Results			Limit
			(1)	(10)	(11)	
Hexavalent Chromium (Cr ⁶⁺)	ug/cm ²	0.10	N.D.	N.D.	N.D.	1000

Item	Unit	MDL	Results				Limit
			(14)	(25)	(26)	(35)	
Hexavalent Chromium (Cr ⁶⁺)	ug/cm ²	0.10	N.D.	N.D.	N.D.	N.D.	1000

TEST REPORT

Report No.: LCS190618129AR

Date:2019.08.08

Page 7 of 15

Note:

- MDL = Method Detection Limit
- /= Not apply
- LOQ = Limit of Quantification, The LOQ of Hexavalent chromium is $0.10 \mu\text{g}/\text{cm}^2$
- $\text{mg}/\text{kg} = \text{ppm} = \text{parts per million}$
- N.D.=Not Detected(<MDL or LOQ)
- *The sample is negative for Cr(VI)-The Cr(VI) concentration is below $0.10\mu\text{g}/\text{cm}^2$
The coating is considered a non-Cr(VI) based coating.
- #1 According to RoHS directive 2011/65/EU and its amendments, Lead is exempted in glass of cathode ray tubes, electronic components and fluorescent tubes.
- #2 According to RoHS directive 2011/65/EU and its amendments, Lead is exempted in electronic ceramic parts (e.g. piezoelectronic devices).
- #3 According to RoHS directive 2011/65/EU and its amendments, Lead is exempted as an alloying element in Copper containing up to 4% (40000ppm) by weight.
- #4 According to RoHS directive 2011/65/EU and its amendments, Lead is exempted in high melting temperature type solders (i.e. lead-based alloys containing 85 % by weight or more lead).
- #5 According to the statement provided by the customer, according to RoHS directive 2011/65/EU and its amendments, Lead is exempted as an alloying element in Aluminum containing up to 0.4% (4000ppm) by weight.
- #6 According to the statement provided by the customer, according to RoHS directive 2011/65/EU and its amendments, Cadmium and its compounds in electrical contact is exempted.
- #7 According to the statement provided by the customer, according to RoHS directive 2011/65/EU and its Amendments, Lead is exempted in steel for machining purposes and in galvanised steel containing up to 0.35% (3500ppm) by weight.
- Flow chart appendix is included.
- Photo appendix is included.

TEST REPORT

Report No.: LCS190618129AR

Date:2019.08.08

Page 8 of 15

3) The test results of DBP、BBP、DEHP & DIBP

Item	Unit	MDL	Results					Limit
			13	18	19	20	2	
Dibuytl Phthalate(DBP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000
Benzylbutyl Phthalate(BBP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000
Bis(2-ethylhexyl) Phthalate(DEHP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000
Diispbutyl phthalate(DIBP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000

Item	Unit	MDL	Results					Limit
			3	4	6	7	27	
Dibuytl Phthalate(DBP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000
Benzylbutyl Phthalate(BBP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000
Bis(2-ethylhexyl) Phthalate(DEHP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000
Diispbutyl phthalate(DIBP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000

Item	Unit	MDL	Results			Limit
			28	30	31	
Dibuytl Phthalate(DBP)	mg/kg	50	N.D.	N.D.	N.D.	1000
Benzylbutyl Phthalate(BBP)	mg/kg	50	N.D.	N.D.	N.D.	1000
Bis(2-ethylhexyl) Phthalate(DEHP)	mg/kg	50	N.D.	N.D.	N.D.	1000
Diispbutyl phthalate(DIBP)	mg/kg	50	N.D.	N.D.	N.D.	1000

Item	Unit	MDL	Results			Limit
			34	37	38	
Dibuytl Phthalate(DBP)	mg/kg	50	N.D.	N.D.	N.D.	1000
Benzylbutyl Phthalate(BBP)	mg/kg	50	N.D.	N.D.	N.D.	1000
Bis(2-ethylhexyl) Phthalate(DEHP)	mg/kg	50	N.D.	N.D.	N.D.	1000
Diispbutyl phthalate(DIBP)	mg/kg	50	N.D.	N.D.	N.D.	1000

TEST REPORT

Report No.: LCS190618129AR

Date:2019.08.08

Page 9 of 15

4) The test results of PBBs & PBDEs

Item	Unit	MDL	Results	Limit
			(27)	
Polybrominated Biphenyls (PBBs)				
Monobromobiphenyl	mg/kg	5	N.D.	
Dibromobiphenyl	mg/kg	5	N.D.	
Tribromobiphenyl	mg/kg	5	N.D.	
Tetrabromobiphenyl	mg/kg	5	N.D.	
Pentabromobiphenyl	mg/kg	5	N.D.	
Hexabromobiphenyl	mg/kg	5	N.D.	
Heptabromobiphenyl	mg/kg	5	N.D.	
Octabromobiphenyl	mg/kg	5	N.D.	
Nonabromodiphenyl	mg/kg	5	N.D.	
Decabromodiphenyl	mg/kg	5	N.D.	
Total content	mg/kg	/	N.D.	1000
Polybrominated Diphenylethers (PBDEs)(Mon-Deca)				
Monobromodiphenyl ether	mg/kg	5	N.D.	
Dibromodiphenyl ether	mg/kg	5	N.D.	
Tribromodiphenyl ether	mg/kg	5	N.D.	
Tetrabromodiphenyl ether	mg/kg	5	N.D.	
Pentabromodiphenyl ether	mg/kg	5	N.D.	
Hexabromodiphenyl ether	mg/kg	5	N.D.	
Heptabromodiphenyl ether	mg/kg	5	N.D.	
Octabromodiphenyl ether	mg/kg	5	N.D.	
Nonabromodiphenyl ether	mg/kg	5	N.D.	
Decabromodiphenyl ether	mg/kg	5	N.D.	
Total content	mg/kg	/	N.D.	1000

Remark:

- mg/kg = ppm
- N.D. = Not detected
- MDL=Method detected limited
- Flow chart appendix is included
- Photo appendix is included.

TEST REPORT


Report No.: LCS190618129AR

Date:2019.08.08


Page 10 of 15

Appendix


1. Test Flow chart for Cd/Pb /Hg content



2. Test Flowchart for Cr⁶⁺ content (For non-metal material)



Test Flowchart for Cr⁶⁺ content (For metal material)




TEST REPORT

Report No.: LCS190618129AR

Date:2019.08.08

Page 11 of 15

3. Test Flow chart for PBBs & PBDEs & DBP & BBP & DEHP & DIBP content



The photo of the sample





TEST REPORT

Report No.: LCS190618129AR

Date:2019.08.08

Page 12 of 15




TEST REPORT

Report No.: LCS190618129AR

Date: 2019.08.08

Page 13 of 15




TEST REPORT

Report No.: LCS190618129AR

Date: 2019.08.08

Page 14 of 15




TEST REPORT

Report No.: LCS190618129AR

Date:2019.08.08

Page 15 of 15



***** End of Report *****

Statement:

1. The test report is considered invalidated without approval signature, special seal on the perforation.
2. The result(s) shown in this report refer only to the sample(s) tested.
3. Without written approval of LCS, this report can't be reproduced except in full.
4. The sample(s) and sample information was/were provided by the client who should be responsible for the authenticity which LCS hasn't verified.
5. In case of any discrepancy between the English version and Chinese version of the testing reports(if generated), the Chinese version shall prevail.